

AMENDMENT NO. 4 JULY 2013
TO
IS 4031 (Part 6) : 1988 METHODS OF PHYSICAL TESTS
FOR HYDRAULIC CEMENT

PART 6 DETERMINATION OF COMPRESSIVE STRENGTH OF
HYDRAULIC CEMENT (OTHER THAN MASONRY CEMENT)

(First Revision)

(Page 1, clause 3.1, line 4) — Substitute ‘not less than 65 percent’ for ‘ 65 ± 5 percent’.

(Page 2, clause 5.7, line 2) — Substitute ‘100 ml to 250 ml’ for ‘150 to 200 ml’.